

분석항목 (ITEM)		단위 (UNIT)	측정방법 (TEST METHOD)	ICF					
두께 (Thickness)		μm	ASTM D 2103	20	25	30	40	50	60
젖음도 (Treatment)		Dyne/cm	ASTM D 2578	38	38	38	38	38	38
투명도 (Haze)		%	ASTM D 1003	2.5	3.0	5.0	6.0	9.0	11.0
신장율 (Elongation at Break)	MD	%	ASTM D 882	350	400	450	550	750	900
	TD	%	ASTM D 882	650	650	700	750	850	950
마찰계수 (C.O.F)		외면/외면	ISCMETHOD	0.20	0.20	0.20	0.20	0.20	0.20
열접착 강도 (Adhesive Intensity)		g/15mm	ISCMETHOD	135°C / 850	135°C / 950	135°C / 1000	135°C / 1100	138°C / 1300	141°C / 1500
인장강도 (Tensile Strength)	MD	kgf/mm ²	ASTM D 882	3.0	3.0	3.0	3.0	3.0	3.0
	TD	kgf/mm ²	ASTM D 882	2.0	2.0	2.0	2.0	2.0	2.0